

## TECHNICAL SHEET



# SUNBRELLA PLUS

Boat equipment

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

## OVERALL CHARACTERISTICS

Composition	100 % Sunbrella solution dyed acrylic			
Finish	Resin based anti-fungi coating, water and UV resistant.			
Weave	Canvas			ISO 7211-1
Weight	320		g/m <sup>2</sup>	ISO 2286-1
Width	152		cm	EN 1773

## FABRIC STRENGTH

Oil-repellent properties	5		class /8	ISO 14419
Tensile strength	145	90	daN	ISO 13934-1
Tear strength	3.3	2.1	daN	ISO 13937-1
Elongation at break	37	32	%	ISO 13934-1
Schmerber	1200		mm	ISO 811
Spray test	4-5		class /5	ISO 4920
Air permeability	3.4		l/m <sup>2</sup> /s	ISO 9237

## COLOUR RESISTANCE

Colour fastness UV	7-8		class /8	ISO 105 B02
Colour fastness weather condition	7-8		class /8	ISO 105 B04
Colour fastness under dry friction	5		class /5	ISO 105X12
Colour fastness under wet friction	5		class /5	ISO 105X12

## USE

Roll length	50		lm	
Recommended use	Cockpit cover, spray hood, bimitop, sun awning, flybridge, winter cover			
Guarantee	5		Years	

The values for this product may have a variation of +/-5%.

**SUNACRYL<sup>®</sup>**  
OUTDOOR FIBRE  
by DICKSON

FINISHING  
**CLEANGARD<sup>®</sup>**  
OUTDOOR TREATMENT  
by DICKSON



### Dickson - Constant

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France  
Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - [www.dickson-constant.com](http://www.dickson-constant.com)